

1- CHARACTERISTICS

Top Coat 134 is used for making coating floors.

Brush application.

Top Coat 134 is an orthophatilic, pre accelerated and thixotropic top coat.

2 – PROPERTIES OF LIQUID GEL COAT

Brookfield viscosity (ISO255 – 23°C – SP4)	50 rpm
Gel Time 23°C – 100g tc 134 – 2ml P MEC M50	28 MIN
Specific gravity	1.45 g/cm ³

3 - PACKAGING

Top Coat 134 is available in 25 Kg kegs.

- ◆ Brush application or roller application.
- ◆ Low viscosity and good thixotropy, freedom from drainage on inclined surfaces.
- ◆ Fast rate of cure.

4 - APPLICATION ADVICES

- ◆ Mix the peroxide well, never put under 1% or over 3%. Use of a catalyst type MEKP.
- ◆ **Top Coat 134** is ready to use : check to homogenise the product before the application.

6 - STORAGE CONDITIONS

Minimum storage life : 3 months.

The top coat is subject to the Highly Flammable Liquids Regulations. The product should be stored under cool conditions in closed opaque containers at a temperature not exceeding 25°C. Avoid exposure to heat sources such as direct sunlight